




65 MARRON



	NORMA STANDARD	VALORI PRESCRITTI DALLA NORMA NORM REQUIRED VALUES	VALORI GRANDINETTI GRANDINETTI VALUES
RESISTENZA ALLA FLESSIONE FLEXION RESISTANCE		5 MPa	20x20x1,2 cm = 4,9 MPa
RESISTENZA AL CARICO BREAKING LOAD	UNI EN 13748-1	/	CLASS 1
RESISTENZA ALL'ABRASIONE ABRASION RESISTANCE	UNI EN 13748-1	≤ 30 cm³/ 50 cm²	1,250 cm³/ 50 cm²
ASSORBIMENTO D'ACQUA WATER ABSORPTION	UNI EN 13748-1	8%	1,37%
CLASSE DI RESISTENZA ALLO SCIVOLOSITA' CLASSIFICATION OF ANTISLIP PROPERTIES	Din 51130	/	R9, R11
RESISTENZA AL FUOCO FIRE RESISTANCE	DIN EN 13748-1	A1	A1
PESO SPECIFICO APPARENTE SPECIFIC GRAVITY	DIN EN 13748-1	/	2520 kg/m³
PERCENTUALE CONTENUTO RICICLATO PERCENTAGE OF RECYCLED CONTENT	DT 55.02 edilizia ED 01 200223	/	≥ 75%